

[TEMPORARY STRUCTURES]

PRECONTRAIT®

502 S2

TRANSLUCENT WHITE

WIDTH: 250/267 cm

WEIGHT: 590 g/sqm

JUMBO ROLLS*: ± 350 lm

LENGTHS*: ± 60 lm

[PERMANENT STRUCTURES]

PRECONTRAIT®

702 S2

TRANSLUCENT WHITE

WIDTH: 250/267 cm

WEIGHT: 750 g/sqm

JUMBO ROLLS*: ± 350 lm

LENGTHS*: ± 60 lm



EVENT STRUCTURES



SPORT COVERS

GUARANTEES AND LABELS



502S2



702S2



Anti-capillarity treatment




100% recyclable

ADVANTAGES

- FERRARI® PRÉCONTRAIT® TECHNOLOGY:
 - EXCEPTIONAL LONGEVITY
- U.V. RESISTANCE
- OPTIMUM WEIGHT/STRENGTH RATIO
- BRIGHT WHITE
- EXCEPTIONAL LUMINOSITY
- ANTI-CAPILLARY TREATMENT
- **NEW S2 VARNISH: EXCEPTIONAL CLEANABILITY**
- **ACCESSORIES: PRÉCONTRAIT® 709 (P. 77)**
FERRARI® KEDER (P. 78)
- **EASY MAINTENANCE: FORMULA S (P. 81)**

COLOURS & REFERENCES

(COLOURS ARE INDICATIVE)



Ref. 502-8604S
translucent white

Ref. 702-8604S
translucent white

TECHNICAL SPECIFICATIONS

	PRÉCONTRAIT® 502 S2 TRANSLUCENT	PRÉCONTRAIT® 702 S2 TRANSLUCENT	STANDARDS
YARN	1100 dtex PES HT ANTI-CAPILLARITY TREATED	1100 dtex PES HT ANTI-CAPILLARITY TREATED	TERSUISSE
WEIGHT	590 g/sqm	750 g/sqm	EN ISO 2286-2
WIDTH	250/267 cm other widths available : please consult us	250/267 cm other widths available : please consult us	
TENSILE STRENGTH (WARP/WEFT)	280/280 daN/5 cm	280/280 daN/5 cm	EN ISO 1421
TEAR STRENGTH (WARP/WEFT)	28/28 daN	30/28 daN	DIN 53.363
ADHESION	10/10 daN/5 cm	10/10 daN/5 cm	EN ISO 2411
FINISH	FORMULA S2 FLUORINATED VARNISH WELDABLE	FORMULA S2 FLUORINATED VARNISH WELDABLE	
LIGHT TRANSMISSION	19%	13,5%	NFP 38 511
FLAME RETARDANCY (502S TRANSLUCENT)	M2/NFP 92-507 • TEST 1/NFPA 701 • CSFM T19 • UBC 31-1 • CLASSE A/ASTM E84 • B1/DIN 4102-1 • BS 7837 • GROUP 1/AS/NZS 3837 • 1530.3/AS/NZS • SP METHOD 2205 • CLASSE 2/UNI 9177 • LP7 • M2/UNE 23.727 • VKF 5.3/SN 198898 • LARGE SCALE CAN U2C5 109 • B1/ONORM B3800-1 • ROCT 3044.97		
FLAME RETARDANCY (702S TRANSLUCENT)	M2/NFP 92-507 • TEST 2/NFPA 701 • CSFM T19 • CLASSE A/ASTM E84 • B1/DIN 4102-1 • BS 7837 • GROUP 1/AS/NZS 3837 • 1530.3/AS/NZS • SITAC/SINTEF/ETA/SIS 650082 • B1/ONORM B 3800-1 • LP7 • M2/UNE 23.727 • VKF 5.2/SN 198898 • CLASSE 1/UNI 9177		
HANDLING TEMPERATURE RANGE	-30°C/+70°C	-30°C/+70°C	
QUALITY MANAGEMENT SYSTEM			ISO 9001

The technical characteristics shown are average values given as a guide and may be modified.
*Our packaging data are given for information only and may vary as a function of manufacturing conditions.